

E.M.GROUT-CL NON-SHRINK CEMENT BASED GROUTING MORTAR

DESCRIPTION

E.M.GROUT-CL is a non-shrink cementitious ready-mix grout with high compressive strength. Due to the special combination of E.M.GROUT-CL, it is useful for filling and grouting of base plates in steel structures and installation of heavy machineries with more than 100 mm grouting height.

FIELD OF APPLICATION

- Filling and grouting of base plates in steel structures
- Installation of heavy machinery
- Installation precast columns
- Anchor bolts

ADVANTAGES

- Suitable for static loads
- No hardening crack
- Non-shrinkage
- Premixed grout requires only the addition of mixing water on site
- Excellent flowability
- High early strength and fast load bearing capacity

SURFACE PREPARATION

Surfaces should be clean sound and free from oil, grease, laitance and loose particles. Metal surfaces should also be clean and free of rust, oil, grease and contaminants. The prepared areas should be flooded with water prior to the placement of E.M.GROUT-CL before the grout is placed. All free water should be released from the area to be grouted. There should be NO standing water present when the grout is placed.

MIXING

E.M.GROUT-CL should be mixed using a suitable mixer. For flowable consistency use a band drill and paddle with a speed of <400 rpm. For large works use a high shear vane grout mixer. The entire contents of the bag should be added to the pre-measured (2.625-3.250 liters) water while mixing. DO NOT add more than the maximum water content.

APPLICATION

Ensure the substrate is prepared according to the manufactures recommendations. NO free water should be present in the area to be grouted. Ensure that there are sufficient air release holes for entrained air to escape.

Mortar should be continuously poured, from one side only, until the gap is completely filled. Maintain continuous head of grout when pouring.



CURING

It is necessary to cure exposed areas of grout with humidified method for at least 7 days.

PHYSICAL AND CHEMICAL PROPERTIES

Physical state: Powder

Color: Gray

Specific gravity of fresh mortar: $2.30 \pm 0.1 \text{ g/cm}^3$

Chloride ion: No chloride content

STORAGE

Shelf life: 1 year in the original package

Storage condition: should be protected from direct sunlight and moisture. Keep bag in the temperature range between $+10^\circ\text{C}$ and $+30^\circ\text{C}$.

Packing: 25 kg bags

HEALTH AND SAFETY

This product does not contain any substances hazardous to human health and the environment. However, it should not be swallowed and contact with skin and eyes. In case of contact with eyes, rinse immediately with plenty of water. E.M.GROUT-CL is not flammable.

For further information refer to the material safety data sheet. MSDS is available at ABADGARAN website.

TECHNICAL SERVICE

The ABADGARAN INTERNATIONAL GROUP Technical Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

