

ABA TILEGROUT

FINE GROUTING MORTAR (FOR JOINTS OF UP TO 6mm WIDTH)

FIELD OF APPLICATION

Fine grouting mortar, particularly easy to apply, for filling joints in ceramic wall and floor coverings, glass and porcelain mosaics, both indoors and outdoors. The very high filling power and easy wash-ability of ABA TILEGROUT ensures rapid and efficient grouting work. For joints up to 6 mm width.

ADVANTAGES

- brilliant colors
- uniform joint appearance
- high filling power
- easy to apply
- also for use with under-floor heating

SURFACE PREPARATION

The surface and thin-bed mortar, dispersion adhesive or thick-bed mortar (at least 7 days old) must have set sufficiently hard and dry. Scraped joints must first be wetted.

In case of tile covering with a porous or non-scratchproof surface test suitable for ABA TILEGROUT for grouting.

APPLICATION

Stir ABA TILEGROUT into clean, clear water until it is completely free of lumps. Make sure that the grouting mortar has a uniform, homogeneous colour after mixing.

Apply the joint filler using the slurry technique. Wipe over and clean freshly grouted tiles with a damp sponge. Remove the dry film later with a soft cloth. Dampen the freshly grouted joints after 24 hours to prevent surface moisture deficiency.

Floor tiles can be walked on after only 12 hours.

TECHNICAL DATA

Base

Bulk weight

Mixing ratio

Maturing time

Application temperature

Application time

Washable

Ready for foot-traffic

Full load-bearing strength

Temperature resistance

Amount required (kg/m²)

Cement with natural mineral fillers and high-quality synthetic resin powder

Approx. 1.1 g/cm³

Approx. 1 .5 l of water for 5 kg of powder

5 minutes

+5°C to +25°C

Approx. 2 hours

after only 15 minutes, depending on the tiling material
after 12 hours

after 2 days

-20°C to +70°C

0.2-0.8 (depending on the tile size and joint width)



PACKAGING

5 kg plastic bags

STORAGE & SHELF LIFE

Approx. 12 months if stored in a tightly sealed container, in cool and dry conditions. Use product in opened containers as soon as possible.

HEALTH & SAFETY

ABA TILEGROUT contains cement and reacts with water, producing an alkaline solution. Always protect skin and eyes. In case of contact, wash immediately with plenty of water. After eye contact seek medical advice. For further information refer to the material safety data sheet. MSDS is available at ABADGARAN website.

TECHNICAL SERVICE

The ABADGARAN INTERNATIONAL GROUP Technical Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

