ABA TILEGROUT

FINE GROUTING MORTAR (FOR JOINTS OF UP TO 6 mm WIDTH)

Fine grouting mortar, particularly easy to apply, for filling joints in ceramic wall and floor coverings, glass and porcelain mosaics, both indoors and outdoors. The very high filling power and easy wash-ability of ABA TILEGROUT ensures rapid and efficient grouting work.

FIELD OF APPLICATION

For joints up to 6 mm width

ADVANTAGES

- Brilliant colors
- Uniform joint appearance
- High filling power
- Easy to apply
- Also for use with under-floor heating

SURFACE PREPARATION

The surface and thin-bed mortar, dispersion adhesive or thick-bed mortar (at least 7 days old) must have set sufficiently hard and dry. Scraped joints must first be wetted.
In case of tile covering with a porous or non-scratchproof surface test suitable for ABA TILEGROUT for grouting.

APPLICATION

Stir ABA TILEGROUT into clean, clear water until it is completely free of lumps. Make sure that the grouting mortar has a uniform, homogeneous colour after mixing.
Apply the joint filler using the slurry technique. Wipe over and clean freshly grouted tiles with a damp sponge. Remove the dry film later with a soft cloth. Dampen the freshly grouted joints after 24 hours to prevent surface moisture deficiency.
Floor tiles can be walked on after only 12 hours.

TECHNICAL PROPERTIES

Base	Cement with natural mineral fillers and high-quality synthetic
Bulk weight	Approx. 1.1 g/cm^3
Mixing ratio	Approx. 1.5 l of water for 25 kg of powder
Maturing time	5 minutes
Application temperature	+5 °C to +25 °C
Application time	Approx. 2 hours
Washable	after only 15 minutes, depending on the tiling material
Ready for foot-traffic	after 12 hours
Full load-bearing strength	after 2 days
Temperature resistance	–20 °C to +70 °C
Amount required (kg/m^2)	0.2-0.8 (depending on the tile size and joint width)

PACKAGING

5 kg pail

STORAGE & SHELFLIFE

Approx. 12 months if stored in a tightly sealed container, in cool and dry conditions. Use product in opened containers as soon as possible.

HEALTH & SAFETY

ABA TILEGROUT contains cement and reacts with water, producing an alkaline solution. Always protect skin and eyes. In case of contact, wash immediately with plenty of water. After eye contact seek medical advice. For further information refer to the material safety data sheet.
MSDS is available at ABADGARAN website.

TECHNICAL SERVICE

The ABADGARAN INTERNATIONAL GROUP Technical Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

All data presented in this technical datasheet are based on our last researches in ABADGARAN CONSTRUCTION CHEMICALS laboratories and are just as a guide for choosing appropriate material. Therefore users should conduct a sufficient investigation to establish the suitability and conformity of any product for intended uses.