

**ABAGROUT-HP
NON-SHRINK CEMENT BASED GROUTING MORTAR****DESCRIPTION**

ABAGROUT-HP is a non-shrink cementitious ready-mix grout with 85 MPa compressive strength. Due to the special combination of ABAGROUT-HP, it is useful for filling and grouting of base plates in steel frame buildings and installation of heavy machinery up to 100 mm. Due to its' special formulation, ABAGROUT-HP could reach high strength & durability factors.

It meets the requirements of the following standard:

ASTM C1107, EN 1504-3

ADVANTAGES

- Suitable for static loads & resistant to vibration
- High performance properties such as ultra-high strength & high durability
- Excellent flowability
- Excellent slump retention which provides extra working time
- High early strength and fast loading capability
- Non-shrink
- Without hardening crack
- Premixed grout requires only the addition of mixing water on site

APPLICATION

- Filling and grouting of base plates in steel frame buildings
- Installation of heavy machinery
- Installation of precast columns & Anchor bolts
- All areas requiring grouting
- Grouting up to 100 mm

SURFACE PREPARATION

Surfaces should be clean sound and free from oil, grease, laitance and loose particles. Metal surfaces should also be clean and free of rust, oil, grease and contaminants.

The prepared areas should be flooded with water prior to the placement of ABAGROUT-HP before the grout is placed. All free water should be released from the area to be grouted. There should be NO standing water present when the grout is placed.

MIXING

ABAGROUT-HP should be mixed using a suitable mixer. For flowable consistency use a band drill and paddle with a speed of <400 R.P.M. For large works use a high shear vane grout mixer. (Drum mixers are not recommended).

The entire contents of the bag should be added to the pre-measured (2.25-3.0 liters) water while mixing.

DO NOT add more than the maximum water content.



موسسه استاندارد و تحقیقات صنعتی ایران
تائیدیه صلاحیت آزمایشگاه همکار



مرکز ملی تایید صلاحیت ایران
ISO / IEC 17025



مجوز صادرات
به اتحادیه اروپا



استاندارد ملی ایران



APPLICATION

Ensure the substrate is prepared according to the manufactures recommendations. NO free water should be present in the area to be grouted. Ensure that there are sufficient air release holes for entrained air to escape.

Mortar should be continuously poured, from one side only, until the gap is completely filled. Maintain continuous head of grout when pouring.

CURING

It is necessary to cure exposed areas of grout with humidified method for at least 7 days.

PHYSICAL AND CHEMICAL PROPERTIES

Physical state: Powder

Color: Grey

Water by weight of grout: 9-12 %

Specific gravity of fresh mortar: $2.3 \pm 0.1 \text{ g/cm}^3$

Chloride ion: No Chloride content

Max. aggregates size: 5 mm

STORAGE

Shelf life: 1 year in the original package

Storage condition: should be protected from direct sunlight and moisture. Keep bag in the temperature range between $+10^\circ\text{C}$ and $+30^\circ\text{C}$

Packing: 25kg bags

HEALTH AND SAFETY

This product does not contain any substances hazardous to human health and the environment. However, it should not be swallowed and contact with skin and eyes. In case of contact with eyes, rinse immediately with plenty of water. ABAGROUT-HP is not flammable.

For further information, refer to the material safety data sheet. MSDS is available at ABADGARAN website.

TECHNICAL SERVICE

The ABADGARAN INTERNATIONAL GROUP Technical Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

All data presented in this technical datasheet are based on our last researches in ABADGARAN CONSTRUCTION CHEMICALS laboratories and are just as a guide for choosing appropriate material. Therefore, users should conduct a sufficient investigation to establish the suitability and conformity of any product for intended uses.



موسسه استاندارد و تحقیقات صنعتی ایران
تأییدیه صلاحیت آزمایشگاه همکار



مرکز ملی تأیید صلاحیت ایران
ISO / IEC 17025



مجوز صادرات
به اتحادیه اروپا



استاندارد ملی ایران

تهران، خیابان سهروردی شمالی، خیابان شهید قندی غربی، ساختمان شماره ۱۲۴، واحد ۱ | تلفکس: ۸۷۷۵۴

www.abadgarangroup.com

info@abadgarangroup.com



واحد تولیدی نمونه ملی